



# Promastic

## ONE PACK WHITE PRE-MIXED MASTIC

**\* Ready to Use \* Non-Slip \* High Flexibility**

**Promastic** is a premium pre-mixed mastic adhesive. It is a quick grabbing, non-slip, flexible wall tile adhesive, which allows tiling to begin from any position on the wall. **Promastic** exceeds the requirements of the Australian Standard AS 2358-1990.

### SUITABLE TILES

- ♦ Natural Stone
- ♦ Bicottura
- ♦ Monocottura
- ♦ Fully Vitrified
- ♦ Porcelain

### COLOUR

- ♦ White

### INTERIOR/EXTERIOR

- ♦ Walls

### SUITABLE SUBSTRATES

- ♦ Cement Render
- ♦ Brickwork/Blockwork (Cement Rendered)
- ♦ Fibre Cement Sheets (Primed)
- ♦ Plasterboard (Primed)

### PRECAUTIONS

**Promastic** is unsuitable for:

- ♦ bonding moisture sensitive green marble;
- ♦ bonding to MDF board or timber & wax impregnated wood - (Our technical advice - sheet with fibre cement boards);
- ♦ bonding to substrates subject to constant water immersion such as swimming pools;
- ♦ bonding to painted substrates;
- ♦ bonding together two impervious substrates.

### SUBSTRATE PREPARATION & EXPANSION JOINTS

All substrates to be tiled must be flat and true, free from oil, dirt, grease or any other contaminants. Very porous substrates should be primed with **Plastinex** (1 part **Plastinex** mixed with 4 parts water). Incorporate expansion joints in accordance with AS 3958.1 1991.

**Cement Render** : Render to be left with a wood float finish and allowed to cure for 7 days.

**Fibre Cement Sheets** : Fibre cement sheets must be primed with **Plastinex** (1 part **Plastinex** mixed with 4 parts water) and all joints must be taped with PVC duct tape and fixed according to the manufacturer's instructions.

**Plasterboard** : Plasterboard must be fixed as per manufacturer's instructions. Jointing compound must be primed with **Plastinex** (1 part **Plastinex** mixed with 4 parts water).



### MIXING

**Promastic** is premixed and ready for use straight from the bucket.

### OPEN TIME

**Promastic** has an open time of approximately 1 hour, which can be shortened to just a few minutes by the action of sun, wind, high temperatures or highly absorbent surfaces. Dampening or priming the substrate prior to tiling prolongs the open time of the adhesive. Tilers need to constantly check that the adhesive has not formed a surface skin and is still fresh to touch. Adhesive with a surface skin must be always removed and discarded.

### APPLICATION, TOOLS AND ADJUSTABILITY TIME

Always install the tiles in accordance with AS 3958 1:1991 and ensure the backs of the tiles are free of dust. Spread **Promastic** evenly across one square metre at a time with a 6mm notched trowel for walls and a 10mm notched trowel for large wall tiles. The choice of trowel should be governed by the depth of the knobs, grooves or ridges on the back of each tile and the evenness of the substrate. Lay the tiles with a fair pressure and at right angles to the adhesive notched pattern. The final bed of adhesive should be between 2mm and 4mm. Wall tiles should have a finished joint width of 2mm - 4mm. Tiles can be adjusted for approximately 40 minutes after laying.

### COVERAGE

20kgs of **Promastic** will cover approximately 12 square metres with a 6mm notched trowel for walls.

### CURE TIME

**Promastic** cures in approximately 24 hours at 23° C and 50% relative humidity. High density substrates or tiles and temperatures during installation below 10°C will significantly increase the cure time.

### CLEAN UP

Remove excess **Promastic** from the grout joints after 30 minutes and clean the tiles with a damp cloth or sponge. Tools and hands can be cleaned with water while the adhesive is still wet.

### JOINT GROUTING

Depending on environmental conditions, commence grouting after approximately 24 hours. Use **Regular** or **Superior Grout** for grout joints between 3mm to 6mm. Use **Aquapoxy**, a three component anti-acid epoxy grout, if the joints are required to have a good chemical resistance. **Grout Add** may also be mixed with **Regular Grout** to impart extra flexibility, reduce porosity and increase water resistance.

### JOINT GROUTING PRECAUTIONS

**DO NOT** use excessive amounts of water during mixing or initial cleaning as this will cause irregular colour finishes and also weaken the grout. **DO NOT** mix the grout with an electric drill above 300 RPM as this can entrap air into the mix causing grout to dry soft and powdery or with unsightly pin holes in the surface. **All grouts should be Damp Cured for 48 hours.** Refer to the Australian Standard AS 3958 Part 1 Section 5.7.3.

### SHELF LIFE

Twelve months if stored in a dry & elevated position in the original factory sealed packaging.

### PACKAGING

**Promastic** is available in 20kg buckets.

### SPECIFICATION CLAUSE

The wall adhesive shall be Morgan **Promastic** - a high performance tile adhesive complying with all relevant Australian & International technical standards.

### MORGAN QUALITY POLICY STATEMENT

**Promastic** is manufactured and distributed to a quality system based on ISO 9001:2000. **Promastic** is guaranteed for 10 years when installed to the guidelines of AS 3958 Part 1 & 2 and in conjunction with written technical information supplied by **Morgan Ceramic Tile Adhesives**.

### FREE TECHNICAL ADVICE AND MATERIAL SAFETY DATA SHEETS

accounts@morganadhesives.com.au

Technical Helpline: 08 9441 6677 (Response within 24hrs)

USER NOTE Although the technical details and recommendations contained in this brochure correspond to the best of our knowledge and experience, all of the above information must, in every case, be taken as merely indicative and subject to confirmation after long term practical applications: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in any case the user is fully responsible for all consequences deriving from the use of the product.