



Tilefast Regular

OFF WHITE

*** Cost Effective * Easy to Trowel * Good Bond Strength**

Tilefast Regular is an off white adhesive composed of cement, fine graded sands and other special additives. When mixed with water, it becomes an easy to trowel adhesive with good bond strength.

SUITABLE TILES

- ◆ Natural Stone
- ◆ Bicottura

COLOUR

- ◆ Off White

INTERIOR/EXTERIOR

Walls & Floors

SUITABLE SUBSTRATES

- ◆ Concrete/Cement Render
- ◆ Brickwork/Blockwork (Cement Rendered)
- ◆ Over Morgan Waterproof Membrane

PRECAUTIONS

Tilefast Regular is unsuitable for:

- ◆ bonding moisture sensitive green marble;
- ◆ bonding Monocottura or Fully Vitrified Tiles unless **Tilefast Regular** is mixed with **Plastinex**;
- ◆ bonding to MDF board or timber & wax impregnated wood ;
- ◆ bonding to substrates subject to constant water immersion such as swimming pools.

SUBSTRATE PREPARATION & EXPANSION JOINTS


All substrates to be tiled must be flat and true, free from oil, dirt, grease or any other contaminants. Very porous substrates should be primed with **Plastinex** (1 part **Plastinex** mixed with 4 parts water). Incorporate expansion joints in accordance with AS 3958.1 1991.

Concrete : New concrete must be allowed to cure for 6 weeks and should have a wood float finish. Use **Floor Prep** to acid etch an adhesive key into concrete finished with a steel float.

Cement Render : Render to be left with a wood float finish and allowed to cure for 7 days.

MIXING & POT LIFE

Add **Tilefast Regular** to clean water at a ratio of 20kg to 5 litres of water. Mix the adhesive to a smooth paste free from lumps by using a drill that has a speed lower than 300 rpm, or mix by hand. Slacken the adhesive and re-mix after 5 minutes. **Tilefast Regular** has a pot life of approximately 3 hours at 23°C and 50% relative humidity.



OPEN TIME

Tilefast Regular has an open time of approximately 30 minutes, which can be shortened to just a few minutes by the action of sun, wind, high temperatures or highly absorbent surfaces. Dampening or priming the substrate prior to tiling prolongs the open time of the adhesive. Tilers need to constantly check that the adhesive has not formed a surface skin and is still fresh to touch. Adhesive with a surface skin must be always removed and discarded.

APPLICATION, TOOLS & ADJUSTABILITY

Always install the tiles in accordance with AS 3958 1:1991 and ensure the backs of the tiles are free of dust. Spread **Tilefast Regular** evenly across one square metre at a time with a 6mm notched trowel for walls and a 10mm notched trowel for floors. The choice of trowel should be governed by the depth of the knobs, grooves or ridges on the back of each tile and the evenness of the substrate. Lay the tiles with a fair pressure and at right angles to the adhesive notched pattern. The final bed of adhesive should be between 2mm and 4mm. Wall tiles should have a finished joint width of 2mm - 4mm and floor tiles should have a finished joint width of 3mm - 6mm. Tiles can be adjusted for approximately 45 minutes after laying.

COVERAGE

20kgs of **Tilefast Regular** will cover approximately 9 square metres with a 6mm notched trowel for walls and approximately 6 square metres with a 10mm notched trowel for floors.

CURE TIME

Tilefast Regular cures in approximately 24 hours at 23°C and 50% relative humidity. High density substrates or tiles and temperatures during installation below 10°C will significantly increase the cure time.

CLEAN UP

Remove excess **Tilefast Regular** from the grout joints after 30 minutes and clean the tiles with a damp cloth or sponge. Tools and hands can be cleaned with water while the adhesive is still wet.

JOINT GROUTING

Depending on environmental conditions, commence grouting after approximately 12 hours. Use **Regular** or **Superior Grout** for grout joints between 3mm to 6mm. **Morgan Slate & Quarry Grout** should be used for joint sizes between 6mm to 20mm. Use **Aquapoxy**, a three component anti-acid epoxy grout, if the joints are required to have a good chemical resistance. **Grout Add** may also be mixed with **Regular Grout** to impart extra flexibility, reduce porosity and increase water resistance.

JOINT GROUTING PRECAUTIONS

DO NOT use excessive amounts of water during mixing or initial cleaning as this will cause irregular colour finishes and also weaken the grout. **DO NOT** mix the grout with an electric drill above 300 RPM as this can entrap air into the mix causing grout to dry soft and powdery or with unsightly pin holes in the surface. **All grouts should be Damp Cured for 48 hours.** Refer to the Australian Standard AS 3958 Part 1 Section 5.7.3.

SHELF LIFE

Twelve months if stored in a dry & elevated position in the original factory sealed packaging.

PACKAGING

Tilefast Regular is available in 20kg bags.

SPECIFICATION CLAUSE

The wall & floor adhesive shall be Morgan **Tilefast Regular** - a tile adhesive complying with all relevant Australian technical standards.

MORGAN QUALITY POLICY STATEMENT

Tilefast Regular is manufactured and distributed to a quality system based on ISO 9001:2000. **Tilefast Regular** is guaranteed for 10 years when installed to the guidelines of AS 3958 Part 1 & 2 and in conjunction with written technical information supplied by **Morgan Ceramic Tile Adhesives**.

FREE TECHNICAL ADVICE AND MATERIAL SAFETY DATA SHEETS

accounts@morganadhesives.com.au

Technical Helpline: 08 9441 6677 (Response within 24hrs)

USER NOTE Although the technical details and recommendations contained in this brochure correspond to the best of our knowledge and experience, all of the above information must, in every case, be taken as merely indicative and subject to confirmation after long term practical applications: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in any case the user is fully responsible for all consequences deriving from the use of the product.